



We help you shine.™



## TOTAL ECLIPSE™ FLOOR FINISH

PROQUIP NZ LTD - 0800 277 678 - [www.proquipnz.co.nz](http://www.proquipnz.co.nz)



**Total Eclipse** is a clear, non-yellowing formulation that creates an extremely durable and scuff resistant shine. A polyurethane-fortified acrylic co-polymer floor coating especially suited for concrete, stone and similar hard floor surfaces. Self-sealing!

## DIRECTIONS

Read all directions and Safety Data Sheets (SDS) before using.

1. For a floor that has been stripped, properly neutralized, rinsed and allowed to dry thoroughly, apply 5-6 thin coats using a clean synthetic mop. Allow the floor to dry thoroughly between coats and prior to burnishing.
2. Optional: Apply 2 thin coats of floor sealer for old or porous floors or for high traffic areas, then apply 4 coats of finish.
3. For a floor that has been deep scrubbed and allowed to dry thoroughly, apply 1-2 thin coats using a clean synthetic mop. Allow floor to dry thoroughly between coats and prior to burnishing.

## PRODUCT INFO

**Product Code** 138FSE

**Volume** 10 liters

**Shipping Package** 2 x 10 liters

**Pallet Quantity** 48

Distributed By:



**Proquip NZ Ltd**  
 t: 0800 277 678  
 e: [sales@proquipnz.co.nz](mailto:sales@proquipnz.co.nz)  
 w: [www.proquipnz.co.nz](http://www.proquipnz.co.nz)

## SURFACES



## TECHNICAL DATA

<b>Description</b>	Acrylic co-polymer emulsion
<b>Appearance</b>	Milky white
<b>Specular Gloss (60°)</b> ASTM D1455-87 (2008)	> 85
<b>Viscosity (Brookfield)</b> @ 68°F (20°C)	<10 centipoise
<b>Coverage Rate</b>	2500 to 3000 ft <sup>2</sup> /gal 61 to 74 m <sup>2</sup> /liter
<b>Dry Time</b>	About 30 minutes
<b>Buffability</b>	Excellent
<b>Removability</b> ASTM D1792-06	Excellent
<b>VOC</b> 40 CFR Part 59 Subpart C	0.044%
<b>Non-Volatile Solids</b> ASTM D2834-95 (2008)	22%
<b>Fragrance</b>	Slight ammoniacal
<b>Slip Resistance</b> ULTM410	Meets requirements
<b>Shelf Life</b> ASTM D1791-93 (2008)	1 year
<b>Density</b> ASTM D1475-98 (2008)	8.5 lb/gal @ 68°F 1.02 kg/L @ 20°C
<b>Detergent Resistance</b> ASTM D3207-92 (2008)	Excellent
<b>Freeze/Thaw</b> ASTM D3209-93 (2008)	Passes 3 cycles
<b>Container</b>	2.64 US gal/10 L (FSE packaging)



Floor Coating and Finishing materials  
 as to slip resistance only. 42E6

